



7 Rue Edouard Garet
42 160 Andrézieux
France

téléphone 0033 (0)4 77 42 65 90
email info@cfpflex.com

DATA SHEET

Date 22/6/2020

PRODUCT	LIBERTY LASER CLEAR STRETCH S	Laser printable TRANSPARENT A4 / A3 film for white or clear textile
CODE	L402 S	(box of 100 sheets)
DESCRIPTION	Heat-adhesive film on NON adhesive polyester carrier.	
THICKNESS +/-5%	Printable film: 60 microns	Polyester carrier: 100 microns.
USER'S GUIDE	<ol style="list-style-type: none"> 1. Text, photo or image must be printed mirrorwise. 2. Use the Bypass feeding (manual feeding) of the printer, on Glossy 100/120g setting. 3. If wanted, cut out the contours using a plotter with an optical eye function. Set up the blade to cut only the print film, and not the polyester carrier, then weed. 4. Put the printed and weeded face directly on the textile, protect the sheet with baking paper. 5. After a first heatpressing at 160°C / 30 seconds, peel the carrier after cooling, and press a second time at 160°C / 30 seconds, while protecting the print with baking paper. Pressure: 5 bars (70 PSI) on automatic press, maximum pressure on manual press.	
WASHING TEMPERATURE	60°C	
TEXTILES	Cotton - Polyester - Polycotton - Nylon (to be tested before use).	
ADVANTAGES	<ol style="list-style-type: none"> 1. Very quick and cost saving to print with a standard CMYK laser printer 2. A professional soft touch, simple to transfer with one format only to use 3. This stretch version is especially elastic and provides great wear confort 4. A high quality full colors print with no rasterisation/RIP software 5. Great scalability : unit or high volume personalisation 6. Easy to cut out the contours thanks to a plotter with an optical eye function & get small details 7. Transparent carrier allows to place the image accurately on textile. 8. Universal thermoadhesive with excellent proven bonding on most textiles 9. Withstand many washing cycles up to 60°C . 10. Elastic and strong film, doesn't wrinkle after washing. 11. Ecofriendly, water based, solvent and PVC free polyurethane. 12. Low carbon profile manufacturing: all operations made under one roof 13. 100% made in France, out of european raw materials. 14. Last generation machines and exclusive manufacturing process, ensuring competitive prices 	
FURTHER RECOMMENDATIONS	<ol style="list-style-type: none"> 1. Wait 24 hours before washing. 2. Do not use bleach or other aggressive chemical agents. 3. Iron from inside. 4. Store our products in a tempered and dry room, protected from direct sun rays. 	
SAFETY	Inert components, REACH compliant, without PVC, plastifiers, heavy metals, VOC, according to Oekotex Standard 100 Class 1.	
RESUBLIMATION	Do not use on sublimated printed polyester.	
IRON ON (A4 SHEETS)	After mirror cutting with scissors or by plotter, and weeding of contours, place the image or text directly on garment, set the iron on maximum heat. Don't use any steam. Protect carrier with a baking paper. Press strongly, from the center towards the edges. Peel off carrier when cold.	

This document is likely to be modified without notice. Please take contact with our commercial department.